

SRS Wiolan HVX



Zinc-free HVLP-Hydraulic Fluids

November 2016

Characteristics

SRS Wiolan HVX are zinc-free mineral oil based high-VI hydraulic fluids with particularly good viscosity temperature behaviour. Highly solvent refined paraffinic neutral base stocks are used exclusively. SRS Wiolan HV provides maximum efficiency and smooth hydraulic system operation, even with extreme temperature fluctuations or starts at sub-zero temperatures. Optimal wear, corrosion and oxidation protection properties ensure a maximum in operating reliability of hydraulic systems along with increased oil retention times and reduced maintenance costs.

Easy filterability of SRS Wiolan HVX hydraulic fluids is required condition for current hydraulic units, filter clogging is prevented.

Application

SRS Wiolan HVX is especially appropriate to use in hydraulic systems which are exposed to extreme temperature fluctuations. This includes the entire range of mobile hydraulics as well as all outdoor stationary units (scrap metal presses, lock gates, loading equipment, marine hydraulics etc.). The multigrade character of SRS Wiolan HV allow for an extensive product rationalization, to prevent confusion and incorrect use. Ordering and storage within the operation are simplified. SRS Wiolan HVX can be used everywhere where zinc-free HLP or HVLP hydraulic fluids are prescribed.

Performance / Specifications

SRS Wiolan HVX hydraulic fluids are shear stable and outperform the requirements for HVLP hydraulic fluids described in DIN 51 524 Part 3 and by ISO 11158 HV.

Approvals

- Hydraulic oil HVLP acc. DIN 51524 Part 3
- Hydraulic oil HV acc. ISO 11158

SRS Wiolan HVX series are products of the H&R ChemPharm GmbH.

Typical Data	Test Method	SRS Wiolan HVX		
		32	46	68
Designation	DIN 51 502	HVLP 32	HVLP 46	HVLP 68
	DIN EN ISO 6743/4	HV 32	HV 46	HV 68
Density at 15°C g/cm ³	DIN 51 757	0.869	0.873	0.878
Kin. Viscosity at 40°C mm ² /s	DIN EN ISO 3104	32.1	45.7	67.8
Kin. Viscosity at 100°C mm ² /s	DIN EN ISO 3104	6.28	8.13	10.9
Viscosity Index (VI)	DIN ISO 2909	150	152	152
Flash Point COC °C	DIN ISO 2592	212	232	240
Pour Point °C	DIN ISO 3016	-30	-35	-33

The above values may vary within the commercial limits.

Made in Germany